

# NÍSTROJOVÉ OCELI PRO PRÁCI ZA TEPLA

## Rozměrový sortiment k dispozici

Tyčová ocel

## Popis produktu

BÖHLER W400 VMR - vakuově přetavená ocel pro práci za tepla s dobrou pevností za tepla a vynikající houževnatostí.

## Trasa tavení

Airmelted + VAR

## Vlastnosti

- > Houževnatost a tažnost : velmi vysoká
- > Odolnost proti opotřebení : dobré
- > Obrobitelnost : dobré
- > Tvrdost za tepla (červená tvrdost) : dobré
- > Leštitelnost : velmi vysoká
- > Tepelná vodivost : velmi vysoká
- > Mikročistota : velmi vysoká

## Použití

- > Tlakové lití
- > Všeobecné díly pro strojírenství
- > Rychlokovací kování
- > Poloteplé lisování
- > Protlačování
- > Nízkotlaké lití
- > Strojírenství
- > Kování
- > Vstřikování plastů
- > Glasfibre reinforced plastics

## Technické údaje

Označení materiálu		Normy	
1.2340	SEL	#207	NADCA
~T20811	UNS		
~X37CrMoV5-1	EN		
~H11	AISI		
E1810	NADCA		

## Chemické složení

C	Si	Mn	Cr	Mo	V
0,37	0,20	0,30	5,00	1,30	0,50

## Materiálové vlastnosti

	Síla za horka	Horká houevnatost	Odolnost proti opot?ebení za tepla
	★★	★★★★★	★★
	★★	★★★★	★★
	★★	★★★	★★
	★★★	★★★★	★★★
	★★★	★★★	★★★
	★★★★	★★★	★★★★
	★★★	★★★★★	★★★
	★★★★★	★★★★	★★★★★
	★★★	★★★★	★★★★


## Stav dodání

Žiháno	
Tvrlost (HB)	max. 205


## Tepelné zpracování

Annealing		
Teplota	800 na 850 °C	Holding time 6 to 8 hours. Slow, controlled furnace cooling at 10 to 20°C/h (50 to 68 °F/hr) to approx. 600°C (1112°F), further cooling in air.
Žihání na odstranění vnitřního pnutí		
Teplota	600 na 670 °C	For stress relief after extensive machining or for complicated tools. Holding time depending on tool size after complete heating 2 - 6 hours in neutral atmosphere. Slow furnace cooling.
Kalení a popouštění		
Teplota	980 na 990 °C	Holding time after temperature equalization: 15 to 30 minutes; In order to prevent coarsening of the grain, hardening must be carried out at the recommended temperature; Quenching: oil, salt bath (500 - 550°C [930 to 1020 °F]), air, inert gas in vacuum; After hardening, required tempering treatment to achieve desired working hardness (see tempering chart).

## Heat treatment sequence



## Continuous cooling CCT curves




Austenitising temperature: 990°C (1814°F)  
 Holding time: 15 minutes  
 5...100 phase percentages  
 0.15...400 cooling parameter, i.e. duration of cooling  
 from 800 - 500°C (1472-932°F) in  $s \times 10^{-2}$

Table:  
 Sample  $\lambda$  HV10

a	0,15	647
b	0,31	619
c	0,40	590
d	1,10	595
e	3	582
f	8	546
g	23	478
h	40	462
j	65	462
k	90	454
l	180	434
m	400	226


### Quantitative phase diagram



A... Austenite  
B... Bainite  
K... Carbide  
M... Martensite  
P... Pearlite  
RA... Retained austenite

- 1 Edge or face
- 2 Core
- 3 Jominy test: distance from the quenched end

### Tempering chart



Tempering:

Slow heating to tempering temperature immediately after hardening (time in furnace 1 hour for each 0,787 inch (20 mm) of workpiece thickness but at least 2 hours / cooling in air).

It is recommended to temper at least twice.

A third tempering cycle for the purpose of stress relieving may be advantageous.

1st tempering approx. 86°F (30°C) above maximum secondary hardness.

2nd tempering to desired working hardness. The tempering chart shows average tempered hardness values.

3rd for stress relieving at a temperature 86 to 122°F (30 to 50°C) below highest tempering temperature.

Hardening temperature: 990°C (1814°F)  
Specimen size: square 20 mm

## Fyzikální vlastnosti

Teplota (°C)	20
Hustota (kg/dm <sup>3</sup> )	7,8
Tepelná vodivost (W/(m.K))	31,5
Měrná tepelná kapacita (kJ/kg K)	0,46
Měrný elektrický odpor (Ohm.mm <sup>2</sup> /m)	-
Modul pružnosti (10 <sup>3</sup> N/mm <sup>2</sup> )	211

## Tepelná roztažnost

Teplota (°C)	100	200	300	400	500	600
Tepelná roztažnost (10 <sup>-6</sup> m/(m.K))	11	11,17	11,93	12,68	13,98	14,34

For additional specifications and technical requirements, please contact our regional voestalpine BÖHLER sales companies.

*The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.*